

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 281 505 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.02.2003 Bulletin 2003/06

(51) Int Cl.7: B29C 70/48, B32B 3/12

(21) Application number: 02255437.2

(22) Date of filing: 02.08.2002

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Yamaguchi, Eikatsu, c/o Fuji Jukogyo K.K.
Tokyo-to (JP)
• Maruyama, Seiji, c/o Fuji Jukogyo K.K.
Tokyo-to (JP)

(30) Priority: 03.08.2001 JP 2001236673

(74) Representative: W.P. Thompson & Co.
Coopers Building,
Church Street
Liverpool L1 3AB (GB)

(71) Applicant: FUJI JUKOGYO KABUSHIKI KAISHA
Tokyo-To (JP)

(54) A method for forming honeycomb sandwich composite panels

(57) A method for forming a honeycomb sandwich composite panel comprising dry fabrics, an unpermeating-resin film, a non-low-viscosity-resin film, a honeycomb core, a non-low-viscosity resin film, an unpermeating-resin film and dry fabrics, stacked in this order in a mold. The cells of the honeycomb core are sealed by the laminated films. The unpermeating-resin film pre-

vents the excessive permeation of the resin which forms the laminated films into the dry fabrics and to enhance the adhesion of this resin to the honeycomb core by forming proper fillets of the resin of the laminated sealing films. Further, drying process for drying the dry fabrics enables the application of the RTM process to the formation of the honeycomb sandwich composite panel.




FIG. 1

Description**BACKGROUND OF THE INVENTION**5 **Field of the Invention**

[0001] The present invention relates to a lightweight, high-stiffness honeycomb composite panel used in aircraft, automobiles, ships, buildings and general industrial equipment and, more particularly, to a method for forming the honeycomb sandwich composite panel using an RTM (resin transfer molding) process.

10

Description of the Related Art

[0002] In a previously known method for forming a honeycomb sandwich panel, outer panels formed as skins are placed on the top and bottom surfaces of a honeycomb core respectively and are bonded to the honeycomb core with an adhesive applied therebetween under heat and pressure. In another previously known method, prepreg sheets are stacked by hand lay-up operation on the top and bottom surfaces of a honeycomb core respectively, and are bonded to the honeycomb core with an adhesive applied therebetween in a vacuum space established in a vacuum bag enclosing the prepreg sheets and the honeycomb core using a hot press or an autoclave.

[0003] In addition, Japanese Patent Laid-Open No. 295362/1997 describes a method for forming a honeycomb sandwich panel using the RTM process, in which an impregnating resin is prevented from flowing into the cells of a honeycomb core with resin/moisture barrier films formed of a particular macromolecular film.

[0004] A method for forming a honeycomb sandwich composite panel disclosed in JP-A No. 5502968/2000 uses a polyimide film, such as Kapton® commercially available from E.I. du Pont de Nemours and Company, as a bonding barrier layer to prevent the resin impregnated into sheets (prepreg sheets) from flowing into the cells of a honeycomb core when a honeycomb sandwich composite panel is formed.

[0005] A method for forming a honeycomb sandwich composite panel disclosed in JP-A No. 167950/2000 comprises the steps of heating sealing materials and dry fabrics to be bonded to the surfaces of a honeycomb core at the thermosetting temperature of the sealing materials, impregnating the dry fabric with a thermosetting resin, and hardening the thermosetting resin impregnated into the dry fabrics by pressing and heating these under predetermined conditions.

[0006] The known method for forming a honeycomb sandwich composite panel employing the RTM process needs to prevent the resin from flowing into the cells of the honeycomb core. Therefore, the cells of the honeycomb core need to be sealed before thermo-setting the honeycomb core in a mold. Thus, two steps and complicated work are necessary before starting an impregnating process, which is an impediment to cost reduction.

[0007] The method for forming a honeycomb sandwich composite panel disclosed in JP-A Nos. 2995362/1997 and 502968/2000 bonds the skins and the honeycomb core together with a resin/moisture-resistant film of a specific polymer and a bonding barrier layer, respectively. Therefore, both the surfaces of the resin/moisture-resistant film and the bonding barrier layer must be coated with an adhesive, which increases the weight of the honeycomb sandwich composite panel. Generally, the specific polymer film is unsatisfactory in adhesive property and incapable of exerting high adhesive strength. Therefore, the film needs to be treated beforehand by a special pretreatment process, which increases processes and provides an impediment to cost reduction.

[0008] Although the method for forming the honeycomb sandwich composite panel disclosed in JP-A No. 167950/2000 is capable of solving the aforementioned problems, this method needs at least two thermo-setting adhesive films and epoxy resin films on the opposite sides of a carrier member, that is this method needs many sealing films.

45

SUMMARY OF THE INVENTION

[0009] The present invention has been made in view of the aforementioned problems, and it is therefore an object of the present invention to provide a method of forming a honeycomb sandwich composite panel capable of forming a reliable sealing layer consisting of a small number of component layers, and of preventing a resin from flowing into the cells of a honeycomb core during an impregnation process and of using a RTM process.

[0010] According to one aspect of the present invention, a method for forming a honeycomb sandwich composite panel includes the steps of: stacking dry fabrics, an unpermeating-resin film, a non-low-viscosity-resin film, a honeycomb core, a non-low-viscosity resin film, an unpermeating-resin film and dry fabrics in this order to form a stacked structure on a lower half mold of a mold; putting an upper half mold of the mold on the stacked structure; clamping together the upper and the lower half mold; closing resin supply ports and air ports formed in the upper and the lower half mold; heating an interior of the mold at a first temperature for a predetermined heating time to cure the unpermeating-resin films and the non-low-viscosity-resin films and to dry the dry fabrics; connecting the air ports of the upper

55

and the lower half mold to an evacuating device; connecting the resin supply ports to a resin supply passage; closing the resin supply passage, and changing a temperature of the interior of the mold to a second temperature while the interior of the mold is evacuated; and supplying an impregnating resin into the mold to impregnate the dry fabrics with the impregnating resin and heating the interior of the mold at a third temperature for a predetermined heating time to cure the impregnating resin supplied into the mold.

[0011] Thus, the honeycomb sandwich composite panel forming method is capable of preventing the impregnating resin from flowing into the cells of the honeycomb core and of forming a honeycomb sandwich composite panel of a satisfactory quality at a low cost.

10 BRIEF DESCRIPTION OF THE DRAWINGS

[0012] By way of example only, specific embodiments of the present invention will now be described, with reference to the accompanying drawings, in which:-

- 15 Fig. 1 is an exploded perspective view of a honeycomb sandwich composite panel formed by the method for forming a honeycomb sandwich composite panel of the present invention;
 Fig. 2 is a fragmentary sectional view of a honeycomb sandwich composite panel formed by the method for forming a honeycomb sandwich composite panel of the present invention;
 Fig. 3 is a diagram showing the steps of a method for forming a honeycomb sandwich composite panel of the present invention; and
 20 Fig. 4 is a diagram showing the steps of second embodiment of the method for forming a honeycomb sandwich composite panel of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

25 [0013] Referring now to Fig. 1, a honeycomb sandwich composite panel 1 formed by a method for forming a honeycomb sandwich composite panel in a first embodiment according to the present invention includes a honeycomb core 2, non-low-viscosity-resin films 3 extended on the opposite surfaces of the honeycomb core 2 respectively, unpermeating-resin films 4 extended on the outer surfaces of the non-low-viscosity-resin films 3 respectively, a plurality of dry fabrics 5 stacked on the outer surface of each of the non-low-viscosity-resin films 4. The non-low-viscosity-resin films 3 and the unpermeating-resin films 4 are constructing sealing members.

[0014] The non-low-viscosity-resin films 3 are resin films that soften when they are heated up to the curing temperature, but do not melt and drip into the cells of the honeycomb core 2 before it is cured, and permit small parts thereof flow along the walls defining the cells of the honeycomb core 2 to form fillets. Resin films suitable for use as the non-low-viscosity-resin films 3 are selected on the basis of test results conducted on a honeycomb core include heating the resin film up to its curing temperature and evaluating the behavior of the resin film during heating up to the curing temperature. Examples of resin films suitable for use as the non-low-viscosity-resin films 3 are MB1515 curable at temperatures in the range of 145 to 180 °C and commercially available from CYTEC Fiberite Inc, FM123-5 curable at temperatures in the range of 115 to 155 °C and commercially available from CYTEC Industries and AF126 and AF126-2 commercially available from Minnesota Mining and Manufacturing Co.

[0015] The unpermeating-resin films 4 are resin films that are cured without permeating into the dry fabrics 5 while the same are heated up to the curing temperature. The unpermeating-resin films 5 having such a property can be prepared by mixing a proper additive in a resin. A resin film suitable for use as the unpermeating-resin films 4 is formed, for example, by adding glass microballoons in a resin in a resin film forming process. A resin film AF325 commercially available from Minnesota Mining and Manufacturing Co. is an example of such a resin film. The inventors of the present invention found that resin films containing glass fibers or nonwoven glass fabrics instead of glass microballoons are suitable for use as the unpermeating-resin films 4. Thus, the non-low-viscosity-resin film 3 and the unpermeating-resin film 4 form a laminated sealing member capable of suppressing the permeation of the resin into the dry fabrics 5 and of reliably forming a film and fillets when heated for curing.

50 [0016] The dry fabrics 5 are impregnated with a thermosetting epoxy resin or a thermosetting polycyanate resin. The honeycomb core 2 and the dry fabrics 5 are the same as those used for forming conventional honeycomb sandwich composite panels.

[0017] The method for forming a honeycomb sandwich composite panel embodying the present invention is now described with reference to Figs. 3 and 4.

55 [0018] Referring to Figs. 3 and 4, the dry fabrics 5 are stacked on a lower half mold of a mold (not shown), the unpermeating-resin film 4 is placed on the dry fabrics 5, the non-low-viscosity-resin film 3 is placed on the unpermeating-resin film 4, the honeycomb core 2 is placed on the non-low-viscosity-resin film 3, the non-low-viscosity resin film 3 is placed on the honeycomb core 2, the unpermeating-resin film 4 is placed on the non-low-viscosity-resin film 3, and

the dry fabrics 5 are stacked on the non-low-viscosity resin film 4 to form a stacked structure on the lower half mold.

[0019] An upper half mold of the mold (not shown) is put on the stacked structure and the upper and the lower half mold are clamped together by a mold clamping mechanism. Then, air discharge ports and resin supply ports formed in the upper and the lower half mold are closed by port-closing devices.

[0020] Then, the upper and the lower half mold and the stacked structure consisting of the component members are heated as shown in Fig. 3 or 4, to impregnate the dry fabrics 5 with an impregnating resin, and to cure the laminated sealing films.

[0021] First, the stacked structure is heated up to a first temperature for curing the laminated sealing films 3, 4 at a heating rate of 1 °C/min, and the stacked structure is kept at the first temperature for a predetermined time to cure the laminated sealing films 3, 4 and to dry the dry fabrics 5.

[0022] Since the mold is sealed before starting the heating process, there is no pressure difference between a space on the inner side of the laminated sealing film, i.e., the interior of the cells, and a space accommodating the dry fabrics 5, and hence creation of defects, such as pores in the laminated sealing films 3, 4 can be avoided.

[0023] Since each laminated sealing member consists of thermosetting epoxy resin films each having different flowing profiles, namely, the unpermeating-resin film 4 contiguous with the dry fabric 5 and the non-low-viscosity-resin film 3 contiguous with the honeycomb core 2, excessive permeation of the resin forming the unpermeating-resin film 4 into the dry fabrics 5 can be avoided and proper fillets capable of ensuring bonding strength can be formed. The dry fabrics 5 are dried and each of the non-low-viscosity-resin film 3 and the unpermeating-resin film 4 are cured to seal the cells of the honeycomb core 2 by the foregoing steps.

[0024] Subsequently, the port-closing devices are removed to open the air discharge ports and the resin supply ports of the upper and the lower half mold, the opened air discharge ports are connected to a vacuum pressure device for evacuating the interior of the mold, the opened resin supply ports are connected to a resin supply line, and then the resin supply passage is closed.

[0025] Then, the interior of the mold is heated or cooled to a second temperature for impregnating the dry fabrics 5 with an impregnating resin, while the interior of the mold is being evacuated. After the interior temperature of the mold has coincided with the second temperature, the resin supply passage connected to the resin supply ports is opened to inject the impregnating resin into the mold at an injection pressure in the range of 0.2 to 0.3 MPa. Consequently, the dry fabrics 5 are impregnated with the impregnating resin. After the impregnating resin starts to overflow through the air discharge port formed in the upper half mold, the air discharge port is closed. The resin supply line is inspected for the leakage of the resin after the laminated sealing films have been cured to suppress the formation of bubbles in the laminated sealing films.

[0026] Then, the impregnating resin supplied into the mold is heated at a third temperature higher than the second temperature for a predetermined time to cure the impregnating resin. Thus, the honeycomb sandwich composite panel 1 is formed.

[0027] In the honeycomb sandwich composite panel forming method shown in Fig. 4, the second temperature is lower than the first temperature. The first and the second temperatures are dependent on the curing temperature of the laminated sealing films and the temperature of the impregnating resin impregnated into the dry fabrics 5. A honeycomb sandwich composite panel having the necessary strength and satisfactory quality can be formed by either the honeycomb sandwich composite panel forming method shown in Fig. 3 or the honeycomb sandwich composite panel forming method shown in Fig. 4. The first and the second temperatures are selectively determined for further cost reduction and further improvement of quality.

[0028] Laminated sealing films, impregnating resins, and first, second and third temperatures for those laminated sealing films and the resins are tabulated in Table 1.

Table 1

First temperature	Sealing film #1: 45 to 180 °C MB1515 and AF325			
	Sealing film #2: 115 to 155 °C One of FM123-2, FM123-5, AF126 and AF126-2, and AF325			
Second temperature	160 ± 5 °C	55 ± 5 °C	55 ± 5 °C	60 ± 10 °C
Third temperature	180 ± 5 °C	80 to 110 °C	120 ± 5 °C	180 ± 5 °C
RTM resin	Epoxy resin A	Epoxy resin B	Epoxy resin C	Polycyanate resin D
Note:				
A: PR-500 (Minnesota Mining and Manufacturing Co.)				
B: TR-A31 (Toray Industries Inc.)				
C: YER-017, YER-058 (The Yokohama Rubber Co., Ltd.)				
D: NM20 (Nippon Oil Corp.)				

[0029] It goes without saying that the laminated sealing films and the impregnating resins may be other than those shown in Table 1.

[0030] As apparent from the foregoing description, according to the present invention, the cells of the honeycomb core are sealed by the laminated sealing films each consisting of two films respectively formed of different resins respectively having different flowing profiles to prevent the excessive permeation of the resin forming the laminated sealing films into the dry fabrics and to enhance the adhesion of the resin of the laminated sealing films to the honeycomb core by forming proper fillets of the resin of the laminated sealing films, drying of the dry fabrics enables the application of the RTM process to the formation of the honeycomb sandwich composite panel. Thus, the honeycomb sandwich composite panel having a satisfactory quality can be fabricated at a low cost.

[0031] Although the invention has been described in its preferred embodiments with a certain degree of particularity, obviously many changes and variations are possible therein. It is therefore to be understood that the present invention may be practised otherwise than as specifically described herein without departing from the scope thereof.

[0032] This application is based on the Japanese Patent Application No.236673/2001 filed on August 3, 2001, the content of which is herein incorporated by reference.

Claims

1. A method for forming a honeycomb sandwich composite panel comprising the steps of:

stacking dry fabrics, an unpermeating-resin film, a non-low-viscosity-resin film, a honeycomb core, a non-low-viscosity resin film, an unpermeating-resin film and dry fabrics in this order to form a stacked structure on a lower half mold of a mold;
 putting an upper half mold of the mold on the stacked structure and clamping together the upper half mold and the lower half mold;
 closing resin supply ports and air ports formed in the upper and the lower half mold;
 heating an interior of the mold at a first temperature for a predetermined heating time to cure the unpermeating-resin films and the non-low-viscosity-resin films and to dry the dry fabrics;
 connecting the air ports of the upper and the lower half molds to an evacuating device;
 connecting the resin supply ports to a resin supply passage;
 closing the resin supply passage,
 changing a temperature of the interior of the mold to a second temperature while the interior of the mold is evacuated; and
 supplying an impregnating resin into the mold to impregnate the dry fabrics with the impregnating resin; and
 heating the interior of the mold at a third temperature for a predetermined heating time to cure the impregnating resin supplied into the mold.

2. The method for forming a honeycomb sandwich composite panel according to claim 1, wherein the impregnating resin is a thermosetting epoxy resin or a thermosetting polycyanate resin,
 said unpermeating-resin film contains a thermosetting epoxy resin,
 and said non-low-viscosity-resin film is formed of a thermosetting epoxy resin.




FIG. 1




FIG. 2




FIG. 3




FIG. 4



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 02 25 5437

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X,D	EP 1 005 978 A (FUJI HEAVY IND LTD) 7 June 2000 (2000-06-07) * claim 1; figures 1,2; table 1 *	1,2	B29C70/48 B32B3/12
X,D	EP 0 786 330 A (HEXCEL CORP) 30 July 1997 (1997-07-30) * claim 1; figure 1 *	1,2	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B32B
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 13 November 2002	Examiner Dupuis, J-L
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>..... & : member of the same patent family, corresponding document</p>			

EPF FORM 1503 (03.82) (P040211)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 25 5437

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-11-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1005978 A	07-06-2000	JP 2000167950 A	20-06-2000
		EP 1005978 A2	07-06-2000

EP 0786330 A	30-07-1997	AU 1234797 A	07-08-1997
		CA 2195050 A1	30-07-1997
		EP 0786330 A2	30-07-1997
		JP 9295362 A	18-11-1997

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.